

'2000

U - Zr 200 350

Oxidation Kinetics of U-Zr alloy in Air at 200 350

， ， ，

150

가 2 .
200 350 , 200
250 가 가
， 300 350
가 - 2
가 ,
가 .

Abstract

For the Storage safety study of the metallic spent fuel, the kinetic rates of U-Zr alloy were measured. The intermittent measuring method was used for this experiment at 200 350 . The specimens appeared no deformation except surface black oxide formation at 200 250 , but showed some powdering phenomena at 300 350 during the test period. The results showed that the U-Zr alloy was more resistive to oxidation than pure uranium metal.

1.

“

”

[1]

.

가

[2 5]

[6 7]

가

가 2

2.

2

0, 5, 10, 15 %

(1,852 °C)

hearth

2

400 mg

가

200, 250, 300 350 °C 4

3.

3.1

200 350

200 250

가

가

, 300 350
 . 1 4 - 2
 가 1 0 %
 350 °C 10 15 wt% 가
 , 20 U₃O₈
 . 300 °C 350 °C 4.4 44 15 wt%
 가 , 250 °C 350 °C 13 130 15 wt%
 가 . 200 °C
 , 400 15
 wt% 가 .
 가
 가 50 °C
 가 3 가 .
 가 가 7.5 wt% 가 가 , 350 °C 2.4
 wt%/h, 300 °C 0.47 wt%/h, 250 °C 0.18 wt%/h, 200 °C 0.05
 wt%/h , 5.1, 2.6 3.6가
 .
 2 5 wt%
 . 350 °C 46 18 wt%
 가 가 가
 . 350 °C 0.675 wt%/h, 300 °C 0.163 wt%/h, 250 °C 0.030
 wt%/h, 200 °C 0.004 wt%/h ,
 4.1, 5.4 7.5가 .
 3 10 wt%
 . 350 °C 46 13.64 wt%
 가 가 가
 . 350 °C 0.296 wt%/h, 300 °C 0.080 wt%/h, 250 °C 0.008
 wt%/h, 200 °C 0.001 wt%/h ,
 3.7, 10 8 .
 4 15 wt%
 . 350 °C 46 7.551 wt%
 가 가 가
 . 350 °C 0.164 wt%/h, 300 °C 0.048 wt%/h, 250 °C
 0.005 wt%/h, 200 °C 0.00034 wt%/h ,
 3.4, 9.6 14.7 .
 가 가
 가 6.5 .
 가 가

가

7.5 wt%

가

Arrhenius plot

1 4

, plot

U metal : $(k) = 3.37 \times 10^5 \exp \left(- \frac{14,970}{R T} \right)$ [wt% / h]

(A.E) = 14.97 [kcal/mol]

U- 5 wt% Zr : $(k) = 1.14 \times 10^7 \exp \left(- \frac{20,510}{R T} \right)$ [wt% / h]

(A.E) = 20.51 [kcal/mol]

U- 10 wt% Zr : $(k) = 5.54 \times 10^7 \exp \left(- \frac{23,340}{R T} \right)$ [wt% / h]

(A.E) = 23.34 [kcal/mol]

U- 15 wt% Zr : $(k) = 8.59 \times 10^7 \exp \left(- \frac{24,590}{R T} \right)$ [wt% / h]

(A.E) = 24.59 [kcal/mol]

3.2 -

5 350 °C -

20 가

가 , 46 가 5

wt% 가 가 , 46

가 5

wt% 가 가 40

가 , 가 10 15 wt%

가 46 가

. 가

2.4, 2.3 1.8 . 가

6 300 °C .

350 °C

가 , 가

3.1, 2.0 1.7 350 °C .

7 250 °C . 6, 3.8

1.7 , 300 350 °C 5 wt%

가 2 .

가 300 °C 250 °C

. 가

8 200 °C .

12.5, 4.1 2.9 250, 300 350 °C

. 가

3.3 -

- 2
 , 1
 200 350 1
 가 9 ,
 , 200 U, U-5 wt% Zr, U- 10 wt% Zr, U- 15 wt% Zr
 0.04075, 0.00380, 0.00091, 0.00037 10.72, 4.17, 2.46
 , 250 0.18685, 0.03059, 0.00976, 0.00455
 6.11, 3.13, 2.14 . 300 0.65675, 0.17119, 0.06928,
 0.03583 3.84, 2.47, 1.93 , 350
 1.88662, 0.72670, 0.35901, 0.20279 2.6, 2.02, 1.77 .

, Matsui [6] 100.3 ± 4.8 KJ/mol, Colmenares [7] 91.45 ± 4.55
 KJ/mol, 97.65 KJ/mol

가

- 2
 가 , 가

가

4.

- 2 200 350

U-5 wt% Zr : $(k) = 1.14 \times 10^7 \exp^{(-20,510/R T)} [wt\% / h]$

(A.E) = 20.51 [kcal/mol]

U- 10 wt% Zr : $(k) = 5.54 \times 10^7 \exp^{(-23,340/R T)} [wt\% / h]$

(A.E) = 23.34 [kcal/mol]

U- 15 wt% Zr : $(k) = 8.59 \times 10^7 \exp^{(-24,590/R T)} [wt\% / h]$

(A.E) = 24.59 [kcal/mol]

- 2

- 2

, 가

가 .

- [1] , “ ”, KAERI/TR-994/98 (1998).
- [2] M.J. Bennett, B.L. Myatt and J.E. Antill, "The oxidation behaviour of highly irradiated uranium in dry carbon dioxide at 375 500 and in dry air at 200 300 ", J. Nucl. Mater. 50, 2 (1974).
- [3] M.J. Bennett, B.L. Myatt, D.R.V. Silvester and J.E. Antill, "The oxidation behaviour of uranium in air at 50 300 ", J. Nucl. Mater. 57, 221 (1975).
- [4] A.G. Ritchie, "A review of the rates of reaction of uranium with oxygen and water vapour at temperatures up to 300 ", J. Nucl. Mater. 102, 170 (1981).
- [5] G.W. McGillivray, D.A. Geeson and R.C. Greenwood, "Studies of the kinetics and mechanism of the oxidation of uranium by dry and moist air", J. Nucl. Mater. 208, 81 (1994).
- [6] Tsuneo Matsui, Takanobu Yamada, Yasushi Ikai and Keiji Naito, "Oxidation of U-20at% Zr alloy in air at 423K-1063K", J. Nucl. Mater. 199, 143 (1993).
- [7] G.A. Rama Rao, V. Venugopal, D.D. Sood, "Oxidation studies on U-Zr alloys", J. Nucl. Mater. 209, 161 (1994).

Researcher	Temp.()	Materials	Activation Energy (kcal/mol)
McGillivray	40 350	U metal	16.0
Bennett	50 100	U metal	18.5
Bennett	100 300	U metal	20.2
Ritchie	40 300	U metal	18.3
Baker	98.5 200	U metal	22.5
Colmenares	117 177	U metal	21.86
G.S.You	150 340	U metal	14.2
G.S.You	183 250	U -Nd alloy	18.6
G.S.You	183 250	U -Nd-Pd alloy	19.9
Matsui	150 230	U -Zr alloy	23.97
Rama Rao	350 527	U -Zr alloy	34.80
This work	200 350	U -Zr alloy	23.34





그림 1. U-0Zr 시편의 각 온도별 산화거동(상) 및 Arrhenius plot(하)





그림 2. U-5Zr 시편의 각 온도별 산화거동(상)
및 Arrhenius plot(하)





그림 3. U-10Zr 시편의 각 온도별 산화거동(상) 및 Arrhenius plot(하)





그림 4. U-15Zr 시편의 각 온도별 산화거동(상) 및 Arrhenius plot(하)




그림 5. U-Zr 시편들의 350 °C에서의 산화거동




그림 6. U-Zr 시편들의 300 °C에서의 산화거동




그림 7. U-Zr 시편들의 250 °C에서의 산화거동




그림 8. U-Zr 시편들의 200 °C에서의 산화거동




그림 9. U 및 U-Zr 합금의 산화율 비교